

Basis	general purpose resin
Resin	AH 120
Hardener	TC 60
Colour	yellowish transparent

Applications

- Vehicle construction
- Laminating resin also for heavy fabrics
- Aircraft construction

Properties

- low viscosity
- high strength
- high heat resistance
- unfilled

Processing data

Product		Mixture AH 120 / TC 60	Resin AH 120	Hardener TC 60
Colour		yellowish transparent	opaque	yellow transparent
Mixing ratio	p. b. w.		100	28
Viscosity at 25°C	mPas	600 ± 100	850 ± 100	55 ± 5
Density at 20°C	g / cm ³	1,10 ± 0,02	1,15 ± 0,03	0,93 ± 0,02
Pot life 200 g / 20°C	min.	60 - 70	-	-
Curing time at RT	hrs.	24	-	-
Post curing	Time in h/ Temperature in °C	4 - 8 / 60 5 - 6 / 80	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	125 ± 10
Flexural elongation at break	EN ISO 178	%	6,8 ± 0,2
Flexural strength	DIN 53452	MPa	-
Flexural modulus	EN ISO 178	MPa	3025 ± 150
Flexural elongation at break	ISO 37	%	-
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	45 ± 7
Compressive strength	EN ISO 604	MPa	90 ± 5
Shore hardness	DIN ISO 7619-1	Shore D	84 ± 3
Heat resistance (HDT)	DIN EN ISO 75 B	°C	102 ± 3
Glass transition temperature T _g	DSC	°C	ca. 94
Coefficient of thermal expansion	internal test / Dilatometer	10 ⁻⁶ K ⁻¹	-
Linear shrinkage	internal	%	-
Compressive strength	DIN 53454	MPa	-

Sales units (packages)

Units	Resin hardener	AH 120 TC 60	5,000 kg / 10,000 kg / 25,000 kg / 50,000 kg / 220,000 kg 1,5 kg / 5 kg / 25 kg / 50 kg
-------	-------------------	-----------------	--

Processing instructions

The temperature of material and processing should be between 18 and 25° C.

The mixing of resin and hardener should be made intensively and if possible without any bubbles at room temperature.

We recommend a post curing with a temperature rise of about 5 - 10°C/hour. Difficult geometries should be supported during the curing cycle. Afterwards the part should be cooled down at about 20°C/hour.

In General

ebalta AH 120/TC 60 is a very thin liquid epoxy resin with high values of strength and dimensional stability. Due to its good impregnating and wetting properties it is suitable as laminating resin for high-strength components with fabrics of glass –or carbon fiber.

ebalta AH 120/TC 60 is suitable for laminating of thin as well as thick laminates with large surface up to a thickness of 8 mm.

A post-curing should be executed, if possible before demoulding.

Storing

At appropriate storage 18-25°C.

Occuring crystallization due to disadvantageous storage conditions can be made return by warming up the material at approx. 60° C for some hours.

Opened containers should be closed immediately after use and be protected against moisture. This material should be used up as soon as possible.

Shelf life: see labels

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.