

Basis	temperature resistant laminating resin
Resin	AH 140
Hardener	TC 60
Colour	Yellowish transparent
Further hardeners	LI 20 / LI 130-1

Applications

- Hand laminating
- Vacuum infusion
- carbon fibre sight laminates
- Laminates for boatbuilding
- Laminates for automotive industry
- Laminates for aeronautic

Properties

- low viscosity
- good curing at room temperature
- high strength
- high heat resistance
- excellent wet-out characteristics

Processing data

Product		Mixture AH 140 / TC 60	Resin AH 140	Hardener TC 60
Colour		Yellowish transparent	transparent	yellow transparent
Mixing ratio	p. b. w.		100	30
Viscosity at 25°C	mPas	600 ± 75	1000 ± 200	55 ± 5
Density at 20°C	g / cm ³	1,10 ± 0,02	1,17 ± 0,02	0,93 ± 0,02
Pot life 200 g / 20°C	min.	55 - 65	-	-
Curing time at RT	hrs.	22 - 26	-	-
Post curing	Time in h/ Temperature in °C	4 - 6 / 60 5 - 6 / 80	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	120 ± 10
Flexural elongation at break	EN ISO 178	%	7,5 ± 0,4
Flexural modulus	EN ISO 178	MPa	2900 ± 300
Flexural elongation at break	ISO 37	%	-
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	50 ± 8
Compressive strength	EN ISO 604	MPa	85 ± 8
Heat resistance (HDT)	DIN EN ISO 75 B	°C	97 ± 3
Glass transition temperature TG	method DSC	°C	ca. 93
Shore hardness	DIN ISO 7619-1	Shore D	86 ± 3
coefficient of thermal expansion	internal test / Dilatometer	10 ⁻⁶ K ⁻¹	-
Linear shrinkage	internal	%	-

Sales units (packages)

Units	Resin hardener	AH 140 TC 60	5,000 kg / 10,000 kg / 25,000 kg / 50,000 kg / 220,000 kg 1,5 kg / 5 kg / 25 kg / 50 kg
-------	-------------------	-----------------	--

Processing instructions

The temperature of material and processing should be between 18 and 25° C.
The mixing of resin and hardener should be made intensively and if possible without any bubbles at room temperature.

Additional details for post curing:

- 24 h at RT
- 4 h at 60°C
- 5 h at 80°C

Storing

At appropriate storage 18-25°C.

Occuring crystallization due to disadvantageous storage conditions can be made return by warming up the material at approx. 60° C for some hours.

Opened containers should be closed immediately after use and be protected against moisture. This material should be used up as soon as possible.

Shelf life is indicated on the labels

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.